



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08B 37/14, A23J 3/14, A21D 2/36, A61L 15/00, A23L 1/00	A1	(11) International Publication Number: WO 98/41547 (43) International Publication Date: 24 September 1998 (24.09.98)
(21) International Application Number: PCT/US98/05549 (22) International Filing Date: 19 March 1998 (19.03.98) (30) Priority Data: 9705739.2 20 March 1997 (20.03.97) GB 9718071.5 28 August 1997 (28.08.97) GB (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: FITCHETT, Colin, Stanley; 13 Sedgwick Street, Cambridge, Cambs CB1 3AJ (GB). GREENSHIELDS, Roderick; 4 Beaconsfield Court, Sketty, Swansea, West Glamorgan SA2 9JU (GB). WEIGHTMAN, Richard, Mark; 3 Swan Close, St. Ives, Huntingdon, Cambs PE17 4HX (GB). (74) Agent: MAJARIAN, William, R.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AL, AM, AU, AZ, BA, BB, BG, BR, BY, CA, CN, CU, CZ, EE, GE, GW, HU, ID, IL, IS, JP, KG, KP, KR, KZ, LC, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UZ, VN, YU, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: IMPROVEMENTS RELATING TO BRAN GELS (57) Abstract Hemicellulosic cereal extracts suitable as substrates for oxidative gelation, gels prepared therefrom, processes for their production, products containing such gels and applications thereof. Preferred sources are wheat sources, when the preparative process may involve the removal of contaminating proteins.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

IMPROVEMENTS RELATING TO BRAN GELS

The present invention relates to hemicellulosic cereal extracts suitable as substrates for oxidative gelation ("gelling hemicelluloses"), to gels prepared therefrom, to processes for their production, to products containing such gels and to various applications thereof. In particular, the present invention relates to an improved process for preparing gelling hemicelluloses from cereals (especially wheat).

The term "hemicellulose" and "hemicellulosic material" are terms of art used to embrace non-cellulosic, non-starch plant polysaccharides. The term therefore embraces *inter alia* pentosans, pectins and gums.

Some hemicelluloses are suitable as substrates for oxidative gelation ("gelling hemicelluloses"): such hemicelluloses often have substituents with phenolic groups which are cross-linkable with certain oxidizing agents.

Arabinoxylan and pectin constitute two particularly important classes of hemicellulose. Arabinoxylans consist predominantly of the pentoses arabinose and xylose, and are therefore often classified as pentosans. However, in many cases hexoses and hexuronic acid are present as minor constituents, and therefore they may also be referred to descriptively as heteroxylans.

The arabinoxylan molecule consists of a linear backbone of (1-4)- β -xylopyranosyl units, to which substituents are attached through O2 and O3 atoms of the xlosyl residues. The major substituents are single α -L-arabinofuranosyl residues. Single α -D-glucoronopyranosyl residues and their 4-O-methyl ethers are also common substituents.

Arabinoxylan preparations are usually heterogeneous with respect to the ratio of xylose to arabinose (i.e., the degree of substitution) and in the pattern of substitution of the arabinosyl units along the (1-4)- β -xylan backbone.

Phenolic acid (including ferulic acid) and acetyl substituents occur at intervals along the arabinoxylan chains. These substituents to some extent determine the solubility of the arabinoxylan. Arabinoxylan preparations bearing phenolic (e.g., ferulic acid substituents) are referred to herein as "AXF", while those bearing acetyl substituents are designated "AXA". Similarly, preparation bearing both phenolic (e.g., ferulic acid) and acetyl substituents are hereinafter abbreviated to the designation "AXFA". Arabinoxylan preparations having few phenolic (e.g., ferulic acid) substituents are designated "AX": when the degree of substitution falls below that required for oxidative gelation, the arabinoxylan is designated a "non-gelling arabinoxylan" (a term which therefore embraces AX and AXA).

Pectins constitute another important class of hemicelluloses. As used herein and unless otherwise indicated, the term "pectin" is used *sensu lato* to define hemicellulose polymers rich in D-galacturonic acid. Many (but not all) are cell wall components. The term "pectin" is also used herein *sensu stricto* to define the so-called "true pectins", which are characterized by the presence of an *O*-(α -D-galacturonopyranosyl)-(1-2)-L-rhamnopyranosyl linkage within the molecule.

The pectins may be subcategorized on the basis of their structural complexity. At one extreme are "simple pectins", which are galacturonans. At the other extreme are "complex pectins" exemplified by rhamnogalacturonan II, which contains at least 10 different monosaccharide components in the main chain or as a components of branches. Pectins of intermediate complexity (herein referred to as "mesocomplex pectins" contain alternate rhamnose and galacturonic acid units, while others have branches of glucuronic acid linked to galacturonic acid.

Complex and mesocomplex pectins are made up of "smooth" regions (based on linear homogalacturonan) and "hairy" regions corresponding to the rhamnogalacturonan backbone with side-branches of varying length.

Certain pectins (for example, pectins obtainable from representatives of the plant family *Chenopodiaceae*, which include beets (e.g., sugar beet), spinach and mangelwurzels) are substituted to some extent with substituents derived from carboxylic acids (usually substituted cinnamic acids) containing phenolic groups. Such pectins may be oxidatively cross-linked to produce viscous solutions or gels *via* their phenolic substituents. This can be achieved by powerful oxidants (e.g., persulfate - see J.-F. Thibault *et alia*, in The Chemistry and Technology of Pectin, Academic Press 1991, Chapter 7, pages 119-133) or a combination of peroxidase and hydrogen peroxide (see Thibault *et alia*, *ibidem*). FR 2 545 101 A1 also describes the gelling of beet pectins using an oxidant (e.g., hydrogen peroxide) and an enzyme (peroxidase). Such pectins are referred to herein as "gelling pectins".

Sugar beet pectin is especially rich in arabinan. Arabinan contains β -1,5-linked arabinose in the backbone with α -(1 \rightarrow 3) or α -(1 \rightarrow 2)-linked arabinose residues, whereas arabinogalactan contains β -1,4-linked galactose in the backbone, with α -(1 \rightarrow 3) or α -(1 \rightarrow 2) linked arabinose residues. Ferulyl substituents are linked to the arabinose and/or the galactose in the arabinan and arabinogalactan side-branches of the rhamnogalacturonan part. The "ferulic acid" content varies according to the extraction method, but is often about 0.6%.

Beet pectins obtained by processes which partially remove arabinose residues may exhibit improved gelling properties. Thus, procedures involving

mild acid treatment and/or treatment with an α -arabinofuranosidase will improve the gelling properties of the pectin (see F. Guillon and J.-F. Thibault, *ibidem*). Such pectins are hereinafter referred to as "treated pectins".

It has long been known that certain flour extracts (e.g., wheat and rye flour extracts) can form gels in the presence of certain oxidants (e.g., upon the addition of hydrogen peroxide). The phenomenon is known in the art as "oxidative gelation", and an extensive literature exists on the subject of oxidative gelation of wheat flour extracts. According to the literature, the gels arise as high molecular weight arabinoxylan and protein molecules become inter- and/or intra-linked (*via inter alia* diferulate bridges) - see e.g., Hosney and Faubion (1981), *Cereal Chem.*, 58:421.

Most of the work in this area has focused on water soluble pentosans from wheat flour. In these studies, wheat flour is extracted with water (usually at room temperature) to yield gelling arabinoxylans. However, water-insoluble wheat pentosans extracted from wheat flours with various concentrations of cold sodium hydroxide have also been shown to form gels (Michniewicz *et alia*, *Cereal Chemistry* 67(5):434-439 (1990).

WO 93/10158 describes the preparation of hemicellulosic material from various brans and the oxidative gelation of maize-derived hemicelluloses using an oxidizing system comprising a peroxide (such as hydrogen peroxide) and an oxygenase (such as a peroxidase). The hemicellulosic material for use as a gelling agent is prepared by hot water or mild alkali extraction.

However, gelling hemicelluloses from some cereal sources (including wheat) produced by known processes form gels which are unsatisfactory for many uses. Such gels are generally opaque, relatively soft, pigmented and exhibit marked syneresis on storage. These properties limit their utility in many potential fields of application (including food technology and the pharmaceutical industry).

There is therefore a need for improved methods of producing gelling hemicelluloses from testaceous cereal fractions (e.g., cereal brans) which exhibit improved gelling characteristics and which do not exhibit these undesirable properties.

It has now been discovered that the undesirable characteristics of the gels produced from certain hemicellulosic bran extracts arise from the presence of contaminating proteins. In certain brans (e.g., many wheat brans and other bran sources which contain residual endosperm material), such proteins are present at concentrations sufficient to impair or prevent the gelation (or to impair the physical properties of the resultant gels). The present inventors have found that substantially reducing the amount of contaminating proteins in the hemicellulosic material prior to gelation makes possible the production of gelling hemicellulose

from a wider range of bran sources (including those previously thought as intractable or unsuitable as starting materials) than has hitherto been possible, and significantly improves the quality of the resultant gels.

This novel finding is particularly surprising in the light of the critical role thought to be played by proteins in the gelling process (see e.g., Hosenev and Faubion (1981), Cereal Chem., 58:421, referred to *infra*).

Thus, according to the present invention there is provided a process for the production of a gelling hemicellulose from a bran containing interfering levels of contaminating protein, the process comprising the steps of extracting hemicellulose from the bran and removing the contaminating protein before and/or after extraction.

As used herein, the term "interfering levels of contaminating protein" refers to concentrations of bran-associated proteins which are sufficient to impair the quality of gels produced by oxidative gelation of hemicellulose extracts prepared therefrom (or prevent or impair gelation of such hemicellulose extracts). In general, protein concentrations of 10% w/w or greater (with respect to the total weight of the bran starting material) are at interfering levels (within the terms of the definition set out above). The contaminating protein is usually endogenous to the bran (i.e., carried over from the milling process), and often comprises or consists of endosperm material. Examples of brans which contain interfering levels of contaminating proteins include many wheat brans and some European corn brans. In many cases, brans which contain interfering levels of contaminating proteins are those which are associated with significant amounts of residual endosperm material.

The contaminating protein need not be removed entirely, but merely to a level sufficient to improve the gelling characteristics or gel quality of the gels ultimately produced. The level of contaminating protein is preferably reduced to a level sufficient to restore or improve the gel (or extract gelling) properties. For example, the contaminating protein concentration may be reduced to below about 15%, 14%, 13%, 12%, 11%, 10%, 9%, 8%, 7%, 6%, 5%, 4%, 3%, 2% or 1%.

The contaminating protein may be removed from the bran by any convenient method, and a wide variety of suitable techniques are known to those skilled in the art. The protein may be removed from the bran itself prior to extraction, from the hemicellulosic bran extract, or from both.

Conveniently, protein removal may include classifying, washing and/or sieving the bran. In such processes, contaminating starch may be removed together with the contaminating protein. In such (dry) techniques, contaminating protein may be removed from the bran as endosperm fragments on the basis of size (e.g., by air classifying, washing or sieving the bran). Preferably, the bran is

sieved through a mesh of 0-250 μm , 250-600 μm , 600-1000 μm and/or greater than 1000 μm . The sieving may be followed by air classification of the sieved bran to remove endosperm fragments, e.g., through a mesh of less than 600 μm (e.g., less than 250 μm). Alternatively, or in addition, contaminating protein may
5 be removed from the bran by washing, for example with hot water or acid (e.g., at a pH of 3-6, e.g., about 5).

Contaminating protein may also be removed from the bran and/or the hemicellulose extract by treatment with a protease. This technique can be applied as the sole protein removal step, or used in any combination with any other
10 method, such as those disclosed herein. In such embodiments, a bran residue may be recovered after protease treatment and the residue washed with hot water or acid (e.g., at a pH of 3-6, e.g., about 5). The protease treatment is conducted for a period of time sufficient to improve the gelling characteristics and/or ultimate quality of the resultant gels, and for example may be conducted for about
15 10-20 min (e.g., about 1 hr), for example at 30-80°C (e.g., about 50°C).

Alternatively, or in addition, contaminating protein may be removed from the hemicellulose extract by heat treating the hemicellulose extract to form a proteinaceous precipitate (for example at 70-100°C, e.g., about 95-100°C, optionally for 5-60 min, e.g., about 20 min). Preferably, such heat treatment
20 comprises the steps heat treating the hemicellulose extract to form a proteinaceous precipitate; removing the precipitate to produce a hemicellulose-enriched supernatant and then recovering gelling hemicellulose from the enriched supernatant.

Other techniques which may be used according to the present invention
25 (alone or in combination with other protein removal steps) include precipitation (e.g., isoelectric precipitation), filtration (e.g., ultrafiltration and/or filtration on vega clay), chromatography (e.g., silica hydrogel and/or ion exchange chromatography) and/or alcohol (e.g., IMS) precipitation, for example with up to 30% v/v alcohol. Particularly preferred is the use of isoelectric precipitation of
30 the hemicellulose extract at a pH of between 2 and 5 (e.g., about 4).

In preferred embodiments, the process comprises the steps of: (a) treating the bran with a protease to yield a bran digest (e.g., under the conditions defined above); (b) extracting hemicellulose from the digest of step (a); (c) heat treating the hemicellulose extract of step (b) to form a proteinaceous precipitate;
35 (d) removing the precipitate of step (c) to produce a hemicellulose-enriched supernatant; (e) recovering gelling hemicellulose from the enriched supernatant of step (d). The bran residue may be recovered after protease treatment and the residue washed with hot water or acid (e.g., at a pH of 3-6, e.g., about 5).

Preferably, the hemicellulose extraction is an alkaline extraction, for example a mild alkaline extraction. For example, the alkaline extraction may be carried out under conditions which do not substantially deferulate polysaccharides (e.g., arabinoxylan) in the hemicellulose. Particularly preferred are alkali
5 extractions conducted with alkali metal hydroxides, such as sodium hydroxide, calcium hydroxide and potassium hydroxide. Calcium hydroxide is particularly advantageous where clear gels are required, because it can be readily precipitated out. The hydroxide is preferably used at about 1-15%, though the optimum amount can be readily determined by routine trial and error by those skilled in the art and depends *inter alia* on the particular bran source used. For example,
10 concentrations of about 5% are useful for many wheat brans, whereas concentrations of about 10% are preferred for maize brans. Particularly preferred for wheat brans is potassium hydroxide at about 5% w/w. The alkaline treatment is preferably carried out for about 10-120 min, for example for about 1 hr. The
15 extraction may be conducted at 30-80°C (e.g., about 60°C).

Preferably, the process further comprises the step of recovering gelling hemicellulose by alcohol precipitation, optionally followed by drying.

A particularly preferred process is shown in schematic form in Fig. 1. Here, "BWB" and "FWB" are abbreviations for broad wheat bran and fine wheat
20 bran, respectively. The "WIP" and "WSP" processes are abbreviations for the water insoluble and water soluble pentosan co-product process respectively. The arrow to the protein deposit shown ("PD") is another important co-product route. The process shown in this figure may further comprise "fine finishing" steps after final trituration in IMS. Such fine finishing may include, for example, starch
25 removal (e.g., by processes comprising centrifugation).

The gelling hemicellulose may comprise a pentosan, e.g., a water soluble or alkali soluble pentosan fraction. Particularly preferred is arabinoxylan, for example arabinoxylan ferulate. For many applications, the gelling hemicellulose will consist of (or consist essentially of) arabinoxylan ferulate.

30 The bran may be any bran in which the level of contaminating protein is sufficiently high so as to interfere with oxidative gelation of hemicellulose extracts prepared therefrom (e.g., by alkaline extraction as described, for example, *infra*). The bran is preferably a cereal bran, for example European corn bran (e.g., German corn bran) or wheat bran.

35 In another aspect, the invention contemplates a process for the production of a hemicellulose gel comprising the steps of: (a) preparing a gelling hemicellulose according to a process as defined in any one of Claims 1-28; and then (b) oxidatively gelling the hemicellulose obtained in step (a) to yield a hemicellulose gel.

The processes of the invention yield useful and important co-products. These include bran derived starch, protein, starch-protein mixtures and the unextracted residue left after extraction of the gelling hemicelluloses. This latter material can be further processed (as described *infra*) to yield a variety of soluble and insoluble pentosan extracts having a wide range of uses in the food industry, the pharmaceutical industry and more generally (e.g., as adhesives or sealants). The protein produced as a by product of the invention has been found to exhibit excellent organoleptic qualities (particularly when digested to varying extents with a protease). Moreover, it has an excellent amino acid profile and is particularly nutritious, being superior to gluten in many respects. Without wishing to be bound by any theory, it is thought that the protein co-products of the invention comprise non-storage protein derived from the endosperm of the plant from which the bran was produced.

Thus, the processes of the invention preferably further comprise the step of recovering the contaminating protein removed from the bran (e.g., in digested form), and may also further comprise the step of recovering contaminating starch removed from the bran (e.g., in admixture with the contaminating protein).

In another aspect, the invention relates to a process for preparing a protein or a mixture of starch and protein comprising the steps of: (a) providing a bran (for example a bran as defined in claim 28); (b) removing protein (and optionally starch) from the bran by processing as defined in any one of Claims 1-28; and (c) recovering the protein (optionally in admixture with starch) removed in step (b); and optionally (d) drying or concentrating the protein (and optionally the starch) recovered in step (c).

The invention also contemplates various products comprising the co-products of the invention. Such co-products may, for example, be formulated as a food, food ingredient, food base, food additive or functional food ingredient comprising the protein co-product of the invention.

The protein co-product may be formulated as: (a) an emulsifier; (b) a binder; (c) a whipping agent; (d) a soya analogue; (e) a milk analogue; (f) a protein isolate or concentrate; (g) a flavouring agent; (h) a dehydrated beverage; (i) a roux or roux blanc; (j) a moisture barrier. For some applications, it is preferred that the protein co-product be at least partially digested, conveniently by the protease treatment applied to the bran or hemicellulose extract in the main product pathway.

The gelling hemicellulose may conveniently be provided in the form of a powder, for example a substantially anhydrous powder and optionally a dispersant (e.g., glucose or maltodextrin). In this form it may further comprise an oxidase,

oxidase substrate (e.g., glucose) and optionally peroxidase supplements, so that the material is self-gelling on the addition of water.

The gelling hemicellulose of the invention may also be provided in the form of an aqueous solution, which is advantageously substantially oxygen free.

5 Such materials may also comprise an oxidase, oxidase substrate (e.g., glucose) and optionally peroxidase supplements, and so also be self-gelling on exposure to oxygen.

The invention also contemplates a gel or viscous medium comprising the gelling hemicellulose of the invention which has been oxidatively gelled. The
10 gelling hemicellulose may comprise (or consist of) cross linked arabinoxylan.

The invention also contemplates a pharmaceutical or cosmetic preparation or medical device comprising the hemicellulosic materials of the invention. The preparation or device may for example be selected from: a wound plug, wound dressing, wound debriding system, controlled release device, an encapsulated
15 medicament or drug, a lotion, cream, suppository, pessary, spray, artificial skin, protective membrane, a neutraceutical, prosthetic, orthopaedic, ocular insert, injectant, lubricant or cell implant matrix. In such embodiments the material, gel or viscous medium of the invention may further comprising an antibiotic, electrolyte, cell, tissue, cell extract, pigment, dye, radioisotope, label, imaging
20 agent, enzyme, co-factor, hormone, cytokine, vaccine, growth factor, protein (e.g., a therapeutic protein), allergen, hapten or antigen (for e.g., sensitivity testing), antibody, oil, analgesic and/or antiinflammatory agent (e.g., NSAID).

The invention also covers the materials of the invention for use in therapy, surgery, prophylaxis or diagnosis, for example in the treatment of surface (e.g.,
25 skin or membrane lesions, e.g., burns, abrasions or ulcers).

In a particularly preferred embodiment, the invention contemplates a wound dressing comprising the material of the invention, for example in the form of a spray. Such wound dressings are particularly useful for the treatment of burns, where their great moisture retaining properties help to prevent the wound
30 drying out. Particularly preferred for such application is the self-gelling liquid of the invention which gels on contact with oxygen in the air. Such compositions can be provided in the form of oxygen-free liquids in airtight containers which can be sprayed onto the skin, whereupon the liquid gels after exposure to the air. Such composition may advantageously be formulated so as to produce a slight excess of
35 hydrogen peroxide on exposure to oxygen, so that a sterilizing, antibacterial, bacteriostatic and/or cleansing effect is obtained which helps promote healing.

The invention also contemplates water absorbant nappies, diapers, incontinence pads, sanitary towels, tampons and panty liners comprising the

materials and gels of the invention, as well as domestic and industrial cleaning or liquid (e.g., water) recovery operations (e.g., in the oil industry).

Alternatively, the gels of the invention can be provided in the form of hydrated or dehydrated sheets or pellicles for application to various internal or external surfaces of the body, for example during abdominal surgery to prevent adhesions. Other embodiments include enzyme immobilizing systems and brewing adjuncts. Also contemplated is a bread improver comprising the material, gel or viscous medium of the invention.

The invention also covers a foodstuff, dietary fibre source, food ingredient, additive, lubricant, supplement or food dressing comprising the material, gel or viscous medium of the invention. Such products are preferably selected from crumb, alginate replacer, cottage cheeses, aerosol toppings, frozen yoghurts, milk shakes, ice cream, low calorie products such as dressings and jellies, batters, cake mixes, frozen chips, binders, gravies, pastas, noodles, doughs, pizza toppings, sauces, mayonnaise, jam, preserve, pickles, relish, fruit drinks, syrups, toppings and confectionary (e.g., soft centres), petfood (wherein the gel e.g., acts as a binder), a flavour delivery agent, a canning gel, fat replacer (e.g., comprising macerated gel of any one of claims), a coating, a glaze, a bait, a binder in meat and meat analogue products (for example vegetarian products), a gelatin replacer or dairy product or ingredient (e.g., a yoghurt supplement). When used as a fat replacer the gel of the invention is preferably macerated to optimize its mouthfeel and fat mimetic properties.

The invention also finds application in the extraction of gelling hemicelluloses from sources other than bran which may contain interfering levels of contaminating protein. The invention may be used to extract essentially any hemicellulose (within the definition set out earlier). In particular, the hemicellulose may be an arabinoxylan, heteroxylan or pectin. In addition, the hemicellulose for use in the processes of the invention may be a synthetic hemicellulose (i.e., a structural analogue of a naturally-occurring hemicellulose synthesised *in vitro* by any chemical/enzymic synthesis or modification). Arabinoxylans, heteroxylans and pectins may also be used. Of the arabinoxylans, particularly preferred are AXFA, AXF, AXA and AX.

Also suitable for use in the invention are pectins, including the true pectins, simple pectins, complex pectins, mesocomplex pectins and gelling pectins (e.g., those obtainable from representatives of the plant family *Chenopodiaceae*, which include beets (e.g., sugar beet), spinach and mangelwurzel). Particularly preferred is sugar beet pectin (for example in the form of sugar beet pulp). Also useful in the invention are treated pectins (as hereinbefore defined).

Examples of sources other than bran which may be used as starting materials according to the invention include any non-cellulosic, non-starch plant polysaccharides. Thus, the processes of the invention find application in the processing *inter alia* of pentosans, pectins and gums.

- 5 Suitable starting materials containing hemicellulose for use in the processes of the invention typically include plant material of various kinds and any part or component thereof.

Plant materials useful as a starting material in the invention include the leaves and stalks of woody and nonwoody plants (particularly monocotyledonous
10 plants), and grassy species of the family Gramineae. Particularly preferred are gramineous agricultural residues, i.e., the portions of grain-bearing grassy plants which remain after harvesting the seed. Such residues include straws (e.g., wheat, oat, rice, barley, rye, buckwheat and flax straws), corn stalks, corn cobs and corn husks.

- 15 Other suitable starting materials include grasses, such as prairie grasses, gamagrass and foxtail. Other suitable sources include dicotyledonous plants such as woody dicots (e.g., trees and shrubs) as well as leguminous plants.

Another preferred source are fruits, roots and tubers (used herein in the botanical sense). The term "fruit" includes the ripened plant ovary (or group
20 thereof) containing the seeds, together with any adjacent parts that may be fused with it at maturity. The term "fruit" also embraces simple dry fruits (follicles, legumes, capsules, achenes, grains, samaras and nuts (including chestnuts, water chestnuts, horsechestnuts etc.)), simple fleshy fruits (berries, drupes, false berries and pomes), aggregate fruits and multiple fruits. The term "fruit" is also intended
25 to embrace any residual or modified leaf and flower parts which contain or are attached to the fruit (such as a bract). Encompassed within this meaning of fruit are cereal grains and other seeds. Also contemplated for use as starting materials are fruit components, including bran, seed hulls and culms, including malt culms. "Bran" is a component of cereals and is defined as a fraction obtained during the
30 processing of cereal grain seeds and comprises the lignocellulosic seed coat as separate from the flour or meal. Other suitable component parts suitable as starting materials include flours and meals (particularly cereal flours and meals, and including nonwoody seed hulls, such as the bracts of oats and rice).

The term "root" is intended to define the usually underground portion of a
35 plant body that functions as an organ of absorption, aeration and/or food storage or as a means of anchorage or support. It differs from the stem in lacking nodes, buds and leaves. The term "tuber" is defined as a much enlarged portion of subterranean stem (stolon) provided with buds on the sides and tips.

Preferred lignocellulosic starting materials include waste stream components from commercial processing of crop materials such as various beets and pulps thereof (including sugar beet pulp), citrus fruit pulp, wood pulp, fruit rinds, nonwoody seed hulls and cereal bran. Suitable cereal sources include
5 maize, barley, wheat, oats, rice, other sources include pulses (e.g., soya), legumes and fruit.

Other suitable starting materials include pollen, bark, wood shavings, aquatic plants, marine plants (including algae), exudates, cultured tissue, synthetic gums, pectins and mucilages.

10 Particularly preferred as a starting material is testaceous plant material, for example waste testaceous plant material (preferably containing at least about 20% of arabinoxylan and/or glucoronoarabinoxylan).

The starting material may be treated directly in its field-harvested state or (more usually) subject to some form of pre-processing. Typical pre-processing
15 steps include chopping, grinding, cleaning, washing, screening, sieving etc.

Applications

The hemicellulose products (i.e., the gels, dehydrated gels, rehydrated dehydrated gels, non-gelling hemicelluloses, gelling (but ungelled) hemicelluloses and viscous liquids of the invention find a variety of applications various
20 therapeutic, surgical, prophylactic, diagnostic and cosmetic (e.g., skin care) applications.

For example, the aforementioned materials may be formulated as a pharmaceutical or cosmetic preparation or medical device, for example selected from: a wound plug, wound dressing, wound debridging system, controlled release
25 device, an encapsulated medicament or drug, a lotion, cream (e.g., face cream), suppository, pessary, spray, artificial skin, protective membrane, a neutraceutical, prosthetic, orthopaedic, ocular insert, injectant, lubricant or cell implant matrix. The non-gelling, gelling and gelled hemicelluloses (e.g., AX, AXF and gelled AXF) are particularly useful as agents which maintain the integrity of the gut wall
30 lining, and as agents for coating the luminal wall of the gastrointestinal tract. They may therefore find particular application in animal feeds and in the treatment of gastrointestinal disorders.

In such embodiments the material, gel or viscous medium of the invention may further comprising an antibiotic, electrolyte, cell, tissue, cell extract, pigment,
35 dye, radioisotope, label, imaging agent, enzyme, co-factor, hormone, cytokine, vaccine, growth factor, protein (e.g., a therapeutic protein), allergen, hapten or antigen (for e.g., sensitivity testing), antibody, oil, analgesic and/or antiinflammatory agent (e.g., NSAID).

Thus, the above-listed materials find application in therapy, surgery, prophylaxis or diagnosis, for example in the treatment of surface (e.g., skin or membrane lesions, e.g., burns, abrasions or ulcers). In a particularly preferred embodiment, the invention contemplates a wound dressing comprising the above listed materials of the invention, for example in the form of a spray. Such wound dressings are particularly useful for the treatment of burns, where their great moisture retaining properties help to prevent the wound drying out.

Particularly preferred for such application is a self-gelling liquid comprising gelling hemicellulose supplemented with glucose and peroxidase and/or oxidase enzymes which gels on contact with oxygen in the air. Such compositions can be provided in the form of oxygen-free liquids in airtight containers which can be sprayed onto the skin, whereupon the liquid gels after exposure to the air. Such composition may advantageously be formulated so as to produce a slight excess of hydrogen peroxide on exposure to oxygen, so that a sterilizing, antibacterial, bacteriostatic and/or cleansing effect is obtained which helps promote healing.

The invention also contemplates water absorbent nappies, diapers, incontinence pads, sanitary towels, tampons and panty liners comprising the above-listed materials, as well as domestic and industrial cleaning or liquid (e.g., water) recovery operations (e.g., in the oil industry).

Alternatively, the gels of the invention can be provided in the form of hydrated or dehydrated sheets or pellicles for application to various internal or external surfaces of the body, for example during abdominal surgery to prevent adhesions.

Other applications include enzyme immobilizing systems, brewing adjuncts and bread improvers.

The materials listed above also find application as a foodstuff, dietary fibre source, food ingredient, additive, lubricant, supplement or food dressing. Such products are preferably selected from crumb, alginate replacer, cottage cheeses, aerosol toppings, frozen yoghurts, milk shakes, ice cream, low calorie products such as dressings and jellies, batters, cake mixes, frozen chips, binders, gravies, pastas, noodles, doughs, pizza toppings, sauces, mayonnaise, jam, preserve, pickles, relish, fruit drinks, a clouding agent in drinks, syrups, toppings and confectionary (e.g., soft centres), petfood (wherein the gel e.g., acts as a binder), a flavour delivery agent, a canning gel, fat replacer (e.g., comprising macerated gel), a coating, a glaze, a bait, a binder in meat and meat analogue products (for example vegetarian products), an edible adhesive, a gelatin replacer or dairy product or ingredient (e.g., a yoghurt supplement).

When used as a fat replacer the gel of the invention is preferably macerated to optimize its mouthfeel and fat mimetic properties.

The ungelled gellable hemicelluloses and the non-gelling hemicelluloses find particular utility as biodegradable gums and adhesives, e.g., for use in the paper and packaging industries.

Nongelling hemicelluloses (for example, AX) also find particular application as stabilizers, thickeners and gelatin replacers. They have excellent mouthfeel and texture when used in, for example, mousses and other dairy products.

The ungelled (but gellable) hemicelluloses (e.g., AXF) find particular application as clouding agents (e.g., in drinks), as film forming agents (e.g., in moisture barriers), glazes, edible adhesives and other functional food ingredients.

The cellulose fibre is usually bleached prior to use. It has high water holding capacity, and dispersions may be sheared to produce highly viscous pastes. Particularly preferred applications for this (co)product include dressings (e.g., as a modified starch replacer), yogurts and coatings (and especially batters), where it may act as a crisping agent.

The protein (co)products of the invention have been found to exhibit excellent organoleptic qualities (particularly when digested to varying extents with a protease). Moreover, they have an excellent amino acid profile and are particularly nutritious, being superior to gluten in many respects. Without wishing to be bound by any theory, it is thought that the protein (co)products of the invention derived from starting materials comprising bran comprise non-storage protein derived from the endosperm of the plant from which the bran was produced.

The protein co-product may be formulated as: (a) an emulsifier; (b) a binder; (c) a whipping agent; (d) a soya analogue; (e) a milk analogue; (f) a protein isolate or concentrate; (g) a flavouring agent; (h) a dehydrated beverage; (i) a roux or roux blanc; (j) a moisture barrier. For some applications, it is preferred that the protein co-product be at least partially digested, conveniently by the protease treatment applied to the starting material (e.g., bran) or hemicellulose extract in the main process stream.

The various other co-products of the invention (including the β -glucan, starch, protein, cellulose, phenolic extracts, lignin, wax, cutin and/or suberin) find application as foods, food ingredients, food bases, food additives or functional food ingredients. They also find application in various forms of therapy (particularly wound healing).

Particularly preferred in the latter respect are the phenolic extracts of the invention, which also find particular utility as flavouring agents (e.g., vanilla flavourings).

Some of the phenolic extracts and/or waxes, cutins and/or suberins find particular utility as pesticides or crop protection agents.

The invention will now be illustrated in more detail by reference to examples, which are for illustrative purposes only and do not limit the scope of the invention.

EXAMPLE 1

10 10 l of sodium acetate buffer (pH 5, 0.02 M) were pre-equilibrated at 50°C and 10 ml of liquid protease (Profix™) was added.

1 kg of fine wheat bran was added to this enzyme solution, and the suspension mixed vigorously for 60 min, maintaining the temperature at 50°C. The bran residue was then washed over a 200 µm sieve, and rinsed with 3 l of hot water. The washings were discarded and the bran residue recovered.

The washed bran residue was then resuspended in 5 l of sodium acetate buffer (pH 5, 0.02 M) at 60°C and mixed continuously, maintaining the temperature at 60°C. 25 g of KOH pellets were then added, and mixing continued for 60 min at 60°C.

20 After 60 min, the mixture was neutralized to pH 7 with acetic acid and filtered to recover liquid. The mixture was then left to stand while a precipitate forms. Alternatively, the mixture may be centrifuged. A clear, dark golden brown supernatant is recovered.

The pH of the supernatant is then brought to pH 4.8 with acetic acid and 1.5 volumes of IMS added. Further acetic acid is added to maintain the pH at 4.8.

Polysaccharides are then recovered by centrifugation and solvent exchange, and the polysaccharides then dried with acetone. Alternatively, any other suitable method of polysaccharide extraction can be employed.

30 The gelling hemicellulose produced by this method yielded firm, clear gels at low concentrations.

EXAMPLE 2

The procedure described in Example 1 was repeated, except that after recovery of polysaccharides, the extract is heated to 50°C (if necessary to disperse) and then held at a temperature of 95-100°C for 20 min. This denatures residual proteins which are removed by centrifugation (or any other suitable separation method).

The gelling hemicellulose produced by this method yielded firm, clear gels at low concentrations.

EXAMPLE 3

The procedure described in Example 1 was repeated, except that immediately before recovery of polysaccharides, the extract is heated to 50°C (if necessary to disperse) and then held at a temperature of 95-100°C for 20 min.

- 5 This denatures residual proteins which are removed by centrifugation (or any other suitable separation method).

The gelling hemicellulose produced by this method yielded firm, clear gels at low concentrations.

EXAMPLE 4

- 10 Oven dried European corn bran was size fractionated by mechanical agitation across 1.0 mm, 600 µm and 250 µm sieves. The distribution of dry matter in each size class was as follows:

	(a)	0-250µm	26%
	(b)	251-600µm	18%
15	(c)	601µm-1.0mm	29%
	(d)	>1.0mm	27%

Without wishing to be bound by theory, the smallest size fraction (a) was thought to be starch.

- 20 The largest two fractions (c and d) representing 56% of the starting material were then further air classified, which separated solid particles of maize endosperm from the bran particles. Clean bran particles represented 85% of the sieved fractions (c and d), i.e., 48% of the starting material.

The clean bran particles were then size reduced until they passed a 250 µm sieve, and this cleaned bran then used for extraction.

- 25 Extraction was carried out with a 10% w/v dispersion of bran and 10% w/w KOH:clean bran (1% w/v KOH). The extraction was carried out with mixing at 70°C for 1 hour after which the suspension was neutralized to pH7 with acetic acid. An aliquot of this crude liquid extract was found to gel in the presence of peroxide/peroxidase to give an opaque red/brown coloured gel.

- 30 The extract was left for about 30 min and the liquid and solid phases separated using Whatman No. 40 filter paper. The liquid phase was recovered, the pH adjusted to 4.8 and 1.5 volumes IMS added to precipitate polysaccharides. The pH was then readjusted to 5 and samples left for 1 hour.

- 35 Solid AXF was recovered by solvent exchange with IMS, finally drying with acetone at 70°C. The dried product, when formulated as a 1% solution at pH7, formed a clear gel on the addition of peroxide/peroxidase.

EXAMPLE 5

Broad wheat bran was sieved to a 500-1700 µm mesh size to remove starch. 300 g of the sieved bran was added to 3500 ml hot (70°C) 0.025 M

sodium acetate-acetic acid buffer (pH 5). 15 g KOH (5% w/w based on bran) was added and the suspension stirred for 60 min at 70°C. The extract was neutralized to pH 7 with glacial acetic acid, filtered through muslin gauze and the filter cake washed with 400 ml hot (70°C) water.

5 The filtrate was then adjusted to pH 4 with concentrated HCl and cooled to 4°C for 2 h and then left at room temperature overnight during which a protein deposit settled out. The suspension was centrifuged (4000 rpm, 30 min, 4°C). The pellets (protein deposits) were frozen and freeze dried.

10 The supernatant was adjusted to pH 4.87 with concentrated HCl or 40% w/v KOH and arabinoxylan precipitated with 1.5 volumes of 99% IMS. The pH was then readjusted to pH 4.87 with concentrated HCl. Precipitates were triturated three times with 99% IMS, filtered through Propex™ 93K and vacuum dried.

15 A 2% solution of the product in water formed a clear, non synerising gel on the addition of peroxide/peroxidase. Similar gels were obtained after centrifugation of the 2% solution (4000 rpm for 30 min), though these gels were lower in starch than those produced from non-centrifuged solutions.

EXAMPLE 6

20 Fine wheat bran was sieved to a 500-1000 µm mesh size to remove starch. 300 g of the sieved bran was added to 3000 ml hot (70°C) 0.025 M sodium acetate-acetic acid buffer (pH 5). 15 g KOH (5% w/w based on bran) was added and the suspension stirred for 60 min at 70°C. The extract was neutralized to pH 7 with glacial acetic acid, filtered through muslin gauze and the filter cake washed with 400 ml hot (70°C) water.

25 The filtrate was then adjusted to pH 4 with concentrated HCl and cooled to 4°C for 1 h and then left at room temperature overnight during which a protein deposit settled out. The suspension was centrifuged (4000 rpm, 30 min, 4°C). The pellets (protein deposits) were frozen and freeze dried.

30 The supernatant was adjusted to pH 4.87 with concentrated HCl or 40% w/v KOH and arabinoxylan precipitated with 1.5 volumes of 99% IMS. The pH was then readjusted to pH 4.87 with concentrated HCl. Precipitates were triturated three times with 99% IMS, filtered through Propex™ 93K and vacuum dried.

35 A 2% solution of the product in water formed a clear, non synerising gel on the addition of peroxide/peroxidase. Similar gels were obtained after centrifugation of the 2% solution (4000 rpm for 30 min), though these gels were lower in starch than those produced from non-centrifuged solutions.

EXAMPLE 7

Broad wheat bran was sieved to a 500-1700 μm mesh size to remove starch. 9.78 kg of the sieved bran was added to 115 l hot (70°C) 0.025 M sodium acetate-acetic acid buffer (pH 5). 0.489 kg KOH (5% w/w based on bran) was added and the suspension stirred for 60 min at 70°C. The extract was neutralized to pH 7 with glacial acetic acid (0.175 l), filtered through muslin gauze and the filter cake washed with 10 l hot (70°C) water.

The filtrate (109 l) was then adjusted to pH 4 with concentrated HCl (0.9 l) and left at room temperature overnight during which a protein deposit settled out. The supernatant (31 l) was decanted and the remaining liquor plus protein deposit (78l) centrifuged (4000 rpm, 30 min). This supernatant was combined with the original (31 l) to give a total volume of 94.l. The pellet (protein deposit) was frozen and freeze dried.

The supernatant was adjusted to pH 4.87 with 40% w/v KOH and arabinoxylan precipitated with 1.5 volumes of 99% IMS. The pH was then readjusted to pH 4.87 with concentrated HCl. Precipitates were triturated three times with 99% IMS, filtered through Propex™ 93K and vacuum dried.

A 2% solution of the product in water formed a clear, non synerising gel on the addition of peroxide/peroxidase.

EXAMPLE 8

The filter cake from the above extraction of Example 7 was suspended in 115 l hot (70°C) water. 1.725 kg KOH (1.5% w/v) was added and the suspension stirred for 1 h at 70°C. The extract was filtered in 25 l aliquots through two thicknesses of muslin gauze and the filter cake washed with hot (70°C) water to yield filtrates and washings which were processed further (see Example 9, below).

The washed solids were resuspended in cold water and made up to a total volume of 90 l with the same. 15 l 35% v/v H_2O_2 was added (equivalent to a final concentration of 13% v/v after pH adjustment) and the pH adjusted to 12.2 with 40% w/v KOH (10l) and the suspension stirred for 2 h at room temperature after which 0.5 volumes 90% IMS was added and the reaction left unstirred at room temperature overnight. The suspension was adjusted to pH 9 with concentrated HCl (9 l) and 25 l aliquots were filtered through two thicknesses of muslin gauze. Each cake was washed three times with 5 l hot (70°C) water, the cakes combined, resuspended in hot (70°C) water and made up to 75 l total volume with the same. The suspension was acidified to pH 5 with concentrated HCl (0.05 l), filtered through two thicknesses of muslin gauze and the solids washed twice with 5 l hot (70°C) water then once with 5 l cold water. The washed product was frozen and freeze dried as a by product useful e.g., as a functional food ingredient.

EXAMPLE 9

The filtrates and washings from Example 8 was adjusted to pH 5 with concentrated HCl. A product was precipitated by adding 1.5 volumes 90% IMS. The precipitate was triturated twice with 90% IMS and once with 99% IMS,
5 filtered through Propex™ 93K and vacuum dried. The product was useful e.g., as an adhesive.

EXAMPLE 10

Fine wheat bran was sieved to a 500-1000 µm mesh size to remove starch. 11.5 kg of the sieved bran was added to 115 l hot (70°C) 0.025 M sodium acetate-acetic acid buffer (pH 5). 0.575 kg KOH (5% w/w based on bran) was added and
10 the suspension stirred for 60 min at 70°C. The extract was neutralized to pH 7 with glacial acetic acid (0.22 l), filtered through muslin gauze and the filter cake washed with 10 l hot (70°C) water.

The filtrate (106 l) was then adjusted to pH 4 with concentrated HCl (1.0 l) and left at room temperature overnight during which a protein deposit settled out.
15 The supernatant was too cloudy to decant, so the whole was centrifuged (4000 rpm, 30 min). The pellet (protein deposit) was frozen and freeze dried.

The supernatant was adjusted to pH 4.87 with 40% w/v KOH and arabinoxylan precipitated with 1.5 volumes of 99% IMS. The pH was then
20 readjusted to pH 4.87 with concentrated HCl. Precipitates were triturated three times with 99% IMS, filtered through Propex™ 93K and vacuum dried.

A 2% solution of the product in water formed a clear, non synerising gel on the addition of peroxide/peroxidase.

EXAMPLE 11

The filter cake from the above extraction of Example 10 was suspended in 115 l hot (70°C) water. 1.725 kg KOH (1.5% w/v) was added and the suspension stirred for 1 h at 70°C. The extract was filtered in 25 l aliquots through two thicknesses of muslin gauze and the filter cake washed with hot (70°C) water to
25 yield filtrates and washings which were processed further (see Example 12, below).
30

The washed solids were resuspended in cold water and made up to a total volume of 100 l with the same. 3.45 l 35% v/v H₂O₂ was added (equivalent to a final concentration of 3% v/v after pH adjustment) and the pH adjusted to 12.2 with 40% w/v KOH and the total volume made up to 115 l with hot (70°C) water.
35 The suspension stirred for 2 h at 70°C then left unstirred at room temperature overnight. 25 l aliquots were filtered through two thicknesses of muslin gauze. Each cake was washed three times with hot (70°C) water, the cakes combined, resuspended in hot (70°C) water and made up to 75 l total volume with the same. The suspension was acidified to pH 5 with concentrated HCl, filtered through two

thicknesses of muslin gauze and the solids washed twice with 5 l hot (70°C) water then once with 5 l cold water. The washed product was frozen and freeze dried as a by product useful e.g., as a functional food ingredient (e.g., as a food thickener or fat replacer).

5

EXAMPLE 12

The filtrates and washings from Example 11 was adjusted to pH 5 with concentrated HCl. A product was precipitated by adding 1.5 volumes 90% IMS. The precipitate was triturated twice with 90% IMS and once with 99% IMS, filtered through Propex™ 93K and vacuum dried. The product is useful e.g., as an adhesive.

10

EXAMPLE 13

German corn bran was sieved to remove starch and ground in a blender. 40 g of the sieved bran was suspended in 400 ml hot (70°C) 0.025 M sodium acetate-acetic acid buffer (pH 5). 3.6 g KOH (9% w/w based on bran) was added and the suspension stirred for 60 min at 70°C. The extract was neutralized to pH 7 with glacial acetic acid and filtered through a muslin gauze.

15

The filtrate was then adjusted to pH 4.87 with glacial acetic acid and the insolubles allowed to settle overnight at room temperature and then centrifuged (4000 rpm, 30 min). The pellets (protein deposits) were frozen and freeze dried.

20

The supernatant was adjusted to pH 4.87 and arabinoxylan precipitated with 1.5 volumes of 99% IMS. Glacial acetic acid was added to the IMS liquor to a final molarity of 0.2 M. The precipitate (thought to comprise arabinoxylan ferulate) was triturated three times with 99% IMS, filtered through Propex™ 93K and vacuum dried.

25

A 2% solution of the product in water formed a firm, clear, non synerising gel on the addition of peroxide/peroxidase.

CLAIMS

1. A process for the production of a gelling hemicellulose from a bran containing interfering levels of contaminating protein, the process comprising the steps of extracting the gelling hemicellulose from the bran and removing the contaminating protein before and/or after extraction.
2. The process of Claim 1 wherein the level of contaminating protein is reduced to below about 15%, 14%, 13%, 12%, 11%, 10%, 9%, 8%, 7%, 6%, 5%, 4%, 3%, 2% or 1%.
3. The process of Claim 1 or Claim 2 wherein contaminating protein is removed from the bran by air classifying, washing and/or sieving the bran.
4. The process of Claim 3 wherein contaminating starch is removed together with the contaminating protein.
5. The process of any one of the preceding claims wherein contaminating protein is removed from the bran as endosperm fragments on the basis of size (e.g., by air classifying, washing or sieving the bran).
6. The process of any one of Claims 3 to 5 wherein the bran is sieved through a mesh of less than 250 μm , 250-600 μm , 600-1000 μm and/or greater than 1000 μm .
7. The process of Claim 6 comprising removing starch by sieving followed by air classification of the sieved bran to remove endosperm fragments.
8. The process of Claim 7 wherein the sieving comprises sieving through a mesh of less than 600 μm (e.g., less than 250 μm).
9. The process of any one of the preceding claims wherein contaminating protein is removed from the bran by washing, for example with hot water or acid (e.g., at a pH of 3-6, e.g., about 5).
10. The process of any one of the preceding claims wherein contaminating protein is removed from the bran and/or the hemicellulose extract by treatment with a protease.
11. The process of Claim 10 wherein contaminating protein is removed from the bran and a bran residue is recovered after protease treatment and the residue washed with hot water or acid (e.g., at a pH of 3-6, e.g., about 5).
12. The process of Claim 10 or 11 wherein the protease treatment is conducted for about 10-20 min (e.g., about 1 hr), for example at 30-80°C (e.g., about 50°C).
13. The process of any one of the preceding claims wherein contaminating protein is removed from the hemicellulose extract by heat treating the hemicellulose extract to form a proteinaceous precipitate (for example at 70-100°C, e.g., about 95-100°C, optionally for 5-60 min, e.g., about 20 min), or for 2-5 min (e.g., if a heat exchanger is used).

14. The process of Claim 13 wherein the contaminating protein is removed from the hemicellulose extract by the steps of:

(a) heat treating the hemicellulose extract to form a proteinaceous precipitate;

5 (b) removing the precipitate of step (a) to produce a hemicellulose-enriched supernatant;

(c) recovering gelling hemicellulose from the enriched supernatant of step (b).

15 15. The process of any one of the preceding claims wherein the contaminating protein is removed (e.g., from the hemicellulose extract) by:

(a) precipitation (e.g., isoelectric precipitation); and/or

(b) filtration (e.g., ultrafiltration and/or filtration on vega clay); and/or

15 (c) chromatography (e.g., silica hydrogel and/or ion exchange chromatography); and/or

(d) alcohol (e.g., IMS) precipitation, for example with up to 30% v/v alcohol.

20 16. The process of Claim 15 wherein the contaminating protein is removed from the hemicellulose extract) by isoelectric precipitation at a pH of between 2 and 5 (e.g., about 4).

17. A process according to Claim 1 comprising the steps of:

(a) treating the bran with a protease to yield a bran digest (e.g., under the conditions defined in Claim 12);

(b) extracting hemicellulose from the digest of step (a);

25 (c) heat treating the hemicellulose extract of step (b) to form a proteinaceous precipitate;

(d) removing the precipitate of step (c) to produce a hemicellulose-enriched supernatant;

30 (e) recovering gelling hemicellulose from the enriched supernatant of step (d).

18. The process of any one of Claim 17 wherein a bran residue is recovered after protease treatment and the residue washed with hot water or acid (e.g., at a pH of 3-6, e.g., about 5).

35 19. The process of any one of the preceding claims wherein the hemicellulose extraction is an alkaline extraction.

20. The process of Claim 19 wherein the alkaline extraction is mild alkaline extraction.

21. The process of Claim 20 wherein the alkaline extraction is carried out under conditions which do not substantially deferulate polysaccharides (e.g., arabinoxylan) in the hemicellulose.
22. The process of Claim 20 or Claim 21 wherein the alkali extraction is conducted with potassium hydroxide at about 1-15% (e.g., about 10%) w/w (for example for about 10-120 min, preferably about 1 hr).
23. The process of Claim 21 or Claim 22 wherein the extraction is conducted at 30-80°C (e.g., about 60°C).
24. The process of any one of the preceding claims further comprising the step of recovering gelling hemicellulose by alcohol precipitation, optionally followed by drying.
25. The process of any one of the preceding claims wherein the gelling hemicellulose comprises a pentosan, e.g., a water soluble or alkali soluble pentosan fraction.
26. The process of Claim 25 wherein the pentosan comprises arabinoxylan, for example arabinoxylan ferulate.
27. The process of Claim 26 wherein the gelling hemicellulose consists (e.g., consists essentially of) arabinoxylan ferulate.
28. The process of any one of the preceding claims wherein the bran is a cereal bran, for example European corn bran or wheat bran.
29. A gelling hemicellulose produced by (or obtainable by) the process as defined in any one of the preceding claims.
30. The gelling hemicellulose of Claim 29, in dehydrated form.
31. The hemicellulose of Claims 29 or 30 in gelled form.
32. A process for the production of a hemicellulose gel comprising the steps of:
- (a) preparing a gelling hemicellulose according to a process as defined in any one of Claims 1-28; and then
 - (b) oxidatively gelling the hemicellulose obtained in step (a) to yield a hemicellulose gel.
33. A hemicellulose gel produced by (or obtainable by) the process of Claim 32.
34. A process according to any one of Claims 1-28 further comprising the step of recovering the contaminating protein removed from the bran (e.g., in digested form).
35. Protein produced by (or obtainable by) the process of Claim 34.
36. A process according to any one of Claims 1-28 further comprising the step of recovering contaminating starch removed from the bran (e.g., in admixture with the contaminating protein).

37. Starch produced by (or obtainable by) the process of Claim 36.
38. A process for preparing a protein or a mixture of starch and protein comprising the steps of:
- (a) providing a bran (for example a bran as defined in Claim 28);
 - 5 (b) removing protein (and optionally starch) from the bran by processing as defined in any one of Claims 1-28; and
 - (c) recovering the protein (optionally in admixture with starch) removed in step (b); and optionally
 - (d) drying or concentrating the protein (and optionally the starch)
 - 10 recovered in step (c).
39. Protein or a mixture of protein and starch produced by (or obtainable by) the process of Claim 38.
40. A food, food ingredient, food base, food additive or functional food ingredient comprising the protein of Claim 39.
- 15 41. The protein of Claim 39 or Claim 40 which is formulated as:
- (a) an emulsifier;
 - (b) a binder;
 - (c) a whipping agent;
 - (d) a soya analogue;
 - 20 (e) a milk analogue;
 - (f) a protein isolate or concentrate;
 - (g) a flavouring agent;
 - (h) a dehydrated beverage;
 - (i) a roux or roux blanc;
 - 25 (j) a moisture barrier.
42. The protein of any one of Claims 39-41 which is at least partially digested, e.g., by the protease treatment as defined in any one of Claims 10-12.
43. The gelling hemicellulose of Claim 29 in the form of a powder, for example a substantially anhydrous powder and optionally a dispersant (e.g.,
- 30 glucose or maltodextrin).
44. The gelling hemicellulose of Claim 43 which comprises oxidase, oxidase substrate (e.g., glucose) and optionally peroxidase supplements, the material being self-gelling on the addition of water.
45. The gelling hemicellulose of Claims 43 or 44 in the form of an
- 35 aqueous solution.
46. The gelling hemicellulose of Claim 45 which is substantially oxygen free.

47. The material of Claim 46 which comprises oxidase, oxidase substrate (e.g., glucose) and optionally peroxidase supplements and which is self-gelling on exposure to oxygen.

5 48. A gel or viscous medium comprising the gelling hemicellulose of any one of Claims 43-47 which has been oxidatively gelled.

49. The gel of Claim 48 wherein the gelling hemicellulose comprises (or consists essentially of) cross linked arabinoxylan.

10 50. A pharmaceutical or cosmetic preparation or medical device comprising the gelling hemicellulose as defined in any one of the preceding claims, the preparation or device being for example selected from: a wound plug, wound dressing, controlled release device, an encapsulated medicament or drug, a lotion, cream, suppository, pessary, spray, artificial skin, protective membrane, a neutraceutical, prosthetic, orthopaedic, ocular insert, injectant, lubricant or cell implant matrix, optionally further comprising an antibiotic, analgesic and/or
15 antiinflammatory agent.

51. The gelling hemicellulose of any one of the preceding claims for use in therapy, prophylaxis or diagnosis, for example in the treatment of skin lesions (e.g., burns, abrasions or ulcers).

20 52. A wound dressing comprising the gelling hemicellulose of any one of the preceding claims, for example in the form of a spray.

53. A bread improver comprising the gelling hemicellulose of any one of the preceding claims.

25 54. A foodstuff, dietary fibre source, food ingredient, additive, lubricant, supplement or dressing comprising the gelling hemicellulose of any one of the preceding claims, for example being selected from a petfood (wherein the gelling hemicellulose e.g., acts as a binder), a flavour delivery agent, a canning gel, fat replacer (e.g., comprising macerated gel of any one of claims), a coating, a glaze, a bait or a gelatin replacer.

30 55. A masking agent comprising the gelling hemicellulose of any one of claims, for example for use in masking semiconductor wafers, etching plates or surfaces to be painted.

56. A process according to any one of Claims 1-28 further comprising the step of collecting the residue remaining after hemicellulose and protein extraction.

35 57. The process of Claim 56 further comprising the steps of: (a) alkali extracting the residue to yield soluble and insoluble fractions, and (b) recovering the insoluble fraction.

58. The process of Claim 57 further comprising the step of bleaching the insoluble fraction to yield an insoluble extract.

59. The process of Claim 56 further comprising the steps of: (a) alkali extracting the residue to yield soluble and insoluble fractions, and (b) recovering the soluble fraction.

60. The process of Claim 59 further comprising the step of recovering (e.g., by precipitation) pentosans from the soluble fraction to yield a soluble pentosan extract.

61. A process for preparing a pentosan extract comprising the steps of:
(a) providing a bran (for example a bran as defined in Claim 28);
(b) removing protein (and optionally starch) from the bran by processing as defined in any one of Claims 1-28; and
(c) extracting gelling hemicellulose from the bran of step (a) or step (b) (for example by processing as defined in any one of Claims 1-28);
(d) collecting the pentosan residue remaining after step (c), and optionally drying or concentrating the pentosan.

62. The process of Claim 61 for preparing an insoluble pentosan extract further comprising the steps of:

(a) alkali extracting the residue to yield soluble and insoluble fractions, and
(b) recovering the insoluble fraction, and optionally
(c) bleaching the insoluble fraction to yield an insoluble pentosan extract.


63. The process of Claim 61 for preparing a soluble pentosan extract further comprising the steps of:

(a) alkali extracting the residue to yield soluble and insoluble fractions,
(b) recovering (e.g., by precipitation) pentosans from the soluble fraction to yield a soluble pentosan extract.

64. A pentosan extract produced by (or obtainable by) the process of any one of Claims 56-63, which is for example formulated as defined in Claim 41 or for use in (or in the form of) the products defined in any one of Claims 50, 52, 53, 54 or 55.

FIG. 1.

EXTRACTION OF SUPERGEL from WHEAT BRAN



INTERNATIONAL SEARCH REPORT

International Application No.

PUS 98/05549

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08B37/14 A23J3/14 A21D2/36 A61L15/00 A23L1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08B A23J A21D A61L A23L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GEISSMANN T. ET AL.: "Composition of the water soluble wheat flour pentosans and their oxidative gelation" LEBENSMITTEL WISSENSCHAFT UND TECHNOLOGIE vol. 6, 1973, DE. pages 59-62, XP002070593	1,2,15, 25-29, 32,33, 48,49
A	GB 2 261 671 A (GB BIOTECHNOLOGY LIMITED) 26 May 1993 see the whole document & WO 93 010 158 A (GB BIOTECHNOLOGY LIMITED) 27 May 1993 cited in the application	1,3-5,7, 19-26, 28-33, 37, 48-52, 54,61,64
-/--		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

7 July 1998

Date of mailing of the international search report

23/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Mazet, J-F

INTERNATIONAL SEARCH REPORT

ional Application No

US 98/05549

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DD 266 960 A (AKADEMIE DER WISSENSCHAFTEN DER DDR) 19 April 1989 see claims see page 2, line 1 - line 20; example 2 ---	1, 29, 35, 38-41, 54
A	C. J. A. VINKX ET AL.: "Physicochemical and functional properties of rye nonstarch polysaccharides. III. Oxidative gelation of a fraction containibg water-soluble pentosans and proteins" CEREAL CHEMISTRY, vol. 68, no. 6, 1991, USA, pages 617-622, XP002070594 see page 617, left-hand column, line 1 - line 23 see page 618, left-hand column, line 36 - line 50 see page 618, right-hand column, line 58 - line 65 see page 621, left-hand column, line 52 - right-hand column, line 26 ---	1, 2, 10, 12, 24, 25, 29, 31-33
A	EP 0 521 707 A (SAN-EI CHEMICAL INDUSTRIES LTD) 7 January 1993 see abstract see page 3, line 1 - line 3 see page 3; example 1 ---	1, 13-16, 29, 35, 54
A	DD 249 627 A (AKADEMIE DER WISSENSCHAFTEN DER DDR) 16 September 1987 see page 2, line 21 - line 26; example 1 ---	34, 35, 38-41
A	WO 96 03440 A (NOVO NORDISK A/S) 8 February 1996 see page 1, line 25 - page 2, line 7 see page 11, line 7 - page 12, line 21; example 1 ---	29-33, 48-52, 54
A	DATABASE WPI Week 8916 Derwent Publications Ltd., London, GB; AN 89-117702 XP002070595 & JP 01 062 303 A (NIPPON SHOKUJIN KAKO KK) , 8 March 1989 see abstract ---	1, 4, 53
A	DATABASE WPI Week 9007 Derwent Publications Ltd., London, GB; AN 90-048354 XP002070596 & JP 02 001 701 A (NISSHIN FLOUR MILLING CO) , 8 January 1990 see abstract ---	1, 3, 9

INTERNATIONAL SEARCH REPORT

onal Application No

P/US 98/05549

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p> DATABASE WPI Week 8316 Derwent Publications Ltd., London, GB; AN 83-37887K XP002070597 & JP 58 041 824 A (NIPPON SHOKUJIN KAKO KK) , 11 March 1983 see abstract </p>	1,4,9,54

INTERNATIONAL SEARCH REPORT

Information on patent family members

Original Application No

US 98/05549

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2261671	A	26-05-1993	BG 98769 A	30-06-1995
			CA 2123602 A	27-05-1993
			EP 0646135 A	05-04-1995
			EP 0612326 A	31-08-1994
			FI 942245 A	13-05-1994
			HU 67479 A,B	28-04-1995
			JP 7501216 T	09-02-1995
			JP 7502057 T	02-03-1995
			NO 941813 A	13-05-1994
			US 5530112 A	25-06-1996
			US 5633032 A	27-05-1997
			AU 2933592 A	15-06-1993
			AU 2948892 A	15-06-1993
			WO 9310157 A	27-05-1993
			WO 9310158 A	27-05-1993
			ZA 9208825 A	21-06-1993
DD 266960	A		NONE	
EP 521707	A	07-01-1993	JP 5007458 A	19-01-1993
			JP 6086643 A	29-03-1994
			JP 5007449 A	19-01-1993
			JP 5244880 A	24-09-1993
			AU 651219 B	14-07-1994
			AU 1867392 A	07-01-1993
			CA 2072684 A	03-01-1993
			DE 69210486 D	13-06-1996
			DE 69210486 T	12-09-1996
			US 5342641 A	30-08-1994
DD 249627	A		NONE	
WO 9603440	A	08-02-1996	AU 3074595 A	22-02-1996
			BR 9508350 A	04-11-1997
			CA 2195640 A	08-02-1996
			CZ 9700205 A	14-05-1997
			EP 0750641 A	02-01-1997
			FI 970274 A	23-01-1997
			JP 10502962 T	17-03-1998